









1.PRODUCT DESCRIPTION

PRODUCT NAME	ACORNPLEX
SIZE(MM)	1250 × 2500
THICKNESS(MM)	15MM
NUMBER OF LAYERS	9 LAYERS
KINDS OF FILM COLOR	DYNEA BROWN FILM
PROCESSING OF EDGE	BROWN COLOR
MATERIALS	FULL FRESH POPLAR
DENSITY	540 KG/M ³
GLUE	MELAMINE W.B.P GLUE
MOISTURE CONTENT	8%-12%
HOT-PRESS TIMES	TWO TIMES HOT-PRESS&SANDING
REUSE	7 TIMES BY FORMWORK

2.TECHNICAL SPECIFICATION

NO	PROPERTY		UNIT	TEST OF METHOD	VALUE OF TEST	RESULT
1	MOISTURE CONTENT		%	EN 322	8.5%	CHECK OUT
2	DENSITY		KG/M ³	EN 323	540	CHECK OUT
3	BONDING QUALITY	BONDING QUALITY	MPA	EN 314	MAX:1.58 MIN.0.78	CHECK OUT
		DAMAGE RATE	%		86%	
4	BENDING MODULUS OF ELASICITY	LONGITUDINAL	MPA	EN 310	6734	CHECK OUT
		LATERAL			5964	
5	BENDING STRENGTH N/MM	LONGITUDINAL	MPA		62.65	CHECK OUT
		LATERAL			53.63	

3. TESTING REPORT

<p>LABORATORY TEST</p>		
<p>INSPECTION PICS</p>		
		
<p>"WE(CAMELPLY LABORATORY), HEREBY CERTIFY THAT THE REPORT ARE TRUE AND CORRECT AND AGAINST STANDARD CE STANDARD(EN322/323/314/310), THAT NO DIFFERENT REPORT OF THE SAME GOODS HAS BEEN OR WILL BE ISSUE.</p>		