










## 1.PRODUCT DESCRIPTION

PRODUCT NAME	FORTUNEPLEX
SIZE(MM)	1250 × 2500
THICKNESS(MM)	20MM
NUMBER OF LAYERS	6 LAYERS
KINDS OF FILM COLOR	CHINA BLACK FILM
PROCESSING OF EDGE	BROWN COLOR
MATERIALS	RECYCLED MATERIALS & 6 LAYERS POPLAR
DENSITY	560 KG/M <sup>3</sup>
GLUE	MR GLUE
MOISTURE CONTENT	8%-14%
HOT-PRESS TIMES	ONE TIMES HOT-PRESS
REUSE	5-6 TIMES BY FORMWORK

## 2.TECHNICAL SPECIFICATION

NO	PROPERTY		UNIT	TEST OF METHOD	VALUE OF TEST	RESULT
1	MOISTURE CONTENT		%	EN 322	8.1 %	CHECK OUT
2	DENSITY		KG/M <sup>3</sup>	EN 323	560	CHECK OUT
3	BONDIN QUALITY	BONDING QUALITY	MPA	EN 314	MAX:1.35 MIN:0.72	CHECK OUT
		DAMAGE RATE	%		68%	
4	BENDING MODULUS OF ELASICITY	LONGITUDINAL	MPA	EN 310	4460	CHECK OUT
		LATERAL			4050	
5	BENDING STRENGTH N/MM	LONGITUDINAL	MPA		48.58	CHECK OUT
		LATERAL			38.35	

### 3. TESTING REPORT

<p><b>LABORATORY TEST</b></p>		
<p><b>INSPECTION PICS</b></p>		
		
<p><b>"WE(CAMELPLY LABORATORY), HEREBY CERTIFY THAT THE REPORT ARE TRUE AND CORRECT AND AGAINST STANDARD CE STANDARD(EN322/323/314/310), THAT NO DIFFERENT REPORT OF THE SAME GOODS HAS BEEN OR WILL BE ISSUE.</b></p>		