









1.PRODUCT DESCRIPTION

PRODUCT NAME	FORTUNEPLY
SIZE(MM)	1250 × 2500
THICKNESS(MM)	21MM
NUMBER OF LAYERS	13 LAYERS
KINDS OF FILM COLOR	DYNEA BROWN FILM
PROCESSING OF EDGE	BROWN COLOR
MATERIALS	FULL HARDWOOD CORE
DENSITY	635 KG/M ³
GLUE	EUROPEAN PHENOLIC GLUE
MOISTURE CONTENT	8%-12%
HOT-PRESS TIMES	TWO TIMES HOT-PRESS&SANDING
REUSE	25 TIMES BY FORMWORK

2.TECHNICAL SPECIFICATION

NO	PROPERTY		UNIT	TEST OF METHOD	VALUE OF TEST	RESULT
1	MOISTURE CONTENT		%	EN 322	8.1%	CHECK OUT
2	DENSITY		KG/M ³	EN 323	635	CHECK OUT
3	BONDIN QUALITY	BONDING QUALITY	MPA	EN 314	MAX:1.74 MIN.0.84	CHECK OUT
		DAMAGE RATE	%		88%	
4	BENDING MODULUS OF ELASICITY	LONGITUDINAL	MPA	EN 310	7650	CHECK OUT
		LATERAL			6993	
5	BENDING STRENGTH N/MM	LONGITUDINAL	MPA		67.6	CHECK OUT
		LATERAL			50.55	

3. TESTING REPORT

LABORATORY TEST		
INSPECTION PICS		
		
<p>"WE(CAMELPLY LABORATORY), HEREBY CERTIFY THAT THE REPORT ARE TRUE AND CORRECT AND AGAINST STANDARD CE STANDARD(EN322/323/314/310), THAT NO DIFFERENT REPORT OF THE SAME GOODS HAS BEEN OR WILL BE ISSUE.</p>		