







## 1.PRODUCT DESCRIPTION

PRODUCT NAME	ACORNPLEX
SIZE(MM)	1250× 2500
THICKNESS(MM)	9MM
NUMBER OF LAYERS	5 LAYERS
KINDS OF FILM COLOR	DYNEA BROWN FILM
PROCESSING OF EDGE	BROWN COLOR
MATERIALS	FULL FRESH POPLAR
DENSITY	535 KG/M <sup>3</sup>
GLUE	MELAMINE W.B.P GLUE
MOISTURE CONTENT	8%-12%
HOT-PRESS TIMES	TWO TIMES HOT-PRESS&SANDING
REUSE	4 TIMES BY FORMWORK

## 2.TECHNICAL SPECIFICATION

NO	PROPERTY		UNIT	TEST OF METHOD	VALUE OF TEST	RESULT
1	MOISTURE CONTENT		%	EN 322	8.5%	CHECK OUT
2	DENSITY		KG/M <sup>3</sup>	EN 323	535	CHECK OUT
3	BONDING QUALITY	BONDING QUALITY	MPA	EN 314	MAX:1.63 MIN:0.72	CHECK OUT
		DAMAGE RATE	%		89%	
4	BENDING MODULUS OF ELASICITY	LONGITUDINAL	MPA	EN 310	7126	CHECK OUT
		LATERAL			438	
5	BENDING STRENGTH N/MM	LONGITUDINAL	MPA		68.38	CHECK OUT
		LATERAL			56.84	

### 3. TESTING REPORT

<p><b>LABORATORY TEST</b></p>		
<p><b>INSPECTION PICS</b></p>		
		
<p><b>"WE(CAMELPLY LABORATORY), HEREBY CERTIFY THAT THE REPORT ARE TRUE AND CORRECT AND AGAINST STANDARD CE STANDARD(EN322/323/314/310), THAT NO DIFFERENT REPORT OF THE SAME GOODS HAS BEEN OR WILL BE ISSUE.</b></p>		