



**MAXBAU**  
MATERIALE

S.C. MAX BAU Materiale S.R.L  
Parc P3 Logistik, Depozit 2,  
Str. Italia 1-7, comuna Chiajna,  
jud. Ilfov, România  
office@maxbau.ro

## 1.PRODUCT DESCRIPTION

PRODUCT BRAND	ANTI-SLIP PLYWOOD
SIZE(MM)	1250 × 2500
MIN THICKNESS (MM)	9 MM
FILM TYPES	FINLAND DYNEA FILM(120g/M <sup>2</sup> )
CORE	BIRCH CORE
PROCESSING OF EDGE	PHENOLIC PAINT
DENSITY	700 KG/M <sup>3</sup>
GLUE	72 HRS PHENOLIC W.B.P GLUE
MOISTURE CONTENT	8%-10%
TIMES OF HOT-PRESS	TWO TIMES HOT-PRESS
TIMES OF SANDING	TWO TIMES SANDING
USAGE	PLATFORM/SCAFFOLDING/TRANSPORTATION

## 2.TECHNICAL SPECIFICATION

NO	PROPERTY		UNIT	TEST OF METHOD	VALUE OF TEST	RESULT
1	MOISTURE CONTENT		%	EN 322	8%	CHECK OUT
2	DENSITY		KG/M <sup>3</sup>	EN 323	700	CHECK OUT
3	BONDING QUALITY	BONDING QUALITY	MPA	EN 314	MAX:1.96 MIN:1.02	CHECK OUT
		DAMAGE RATE	%		96%	
4	BENDING MODULUS OF ELASTICITY	LONGITUDINAL	MPA	EN 310	12014	CHECK OUT
		LATERAL			8477	
5	BENDING STRENGTH N/MM	LONGITUDINAL	MPA		83.29	CHECK OUT
		LATERAL			82.46	

"WE(CAMELWOOD LABORATORY), HEREBY CERTIFY THAT THE REPORT ARE TRUE AND CORRECT AND AGAINST STANDARD CE, THAT NO DIFFERENT REPORT OF THE SAME GOODS HAS BEEN OR WILL BE ISSUE.

### 3. TESTING REPORT

**LABORATORY TEST**



**INSPECTION PICS**



**"WE(CAMELPLY LABORATORY), HEREBY CERTIFY THAT THE REPORT ARE TRUE AND CORRECT AND AGAINST STANDARD CE STANDARD(EN322/323/314/310), THAT NO DIFFERENT REPORT OF THE SAME GOODS HAS BEEN OR WILL BE ISSUE.**